

the fine art of porcelain stoneware

(campione)

glazed porcelain stoneware

Made In The USA









MARAZZI SUSA

(campione)

glazed porcelain stoneware

Made In The USA

Bronze

















Diamond Insert

Nickel



Diamond Insert











































		(MITIITIDIT 0.42) (1	12-31-2013) 12-31-2013)	Hecycled Content						
	MODULAR TI	LE		FLOOR TIL	E DECOS				TRIMS*	
Thickness	31/4"x61/2" (8.2x16.5 cm) 5/16"(8.5 mm)	6½"x6½" (16.5x16.5 cm) 5/16"(8.5mm)	13"x13" (33.3x33.3 cm) 5/16"(8.5mm)	20"x20" (50x50 cm) 7/16"(10.5mm)	13"x13" (33.3x33.3 cm) Mosaic - Octagon 2"x2"	1"x1" (2.5x2.5 cm) Diamond** Insert	2"x2" (5x5 cm) Diamond**	4"x4" (10x10 cm) Diamond** Insert	2"x13" (5x33.3 cm) Chair Rail**	3"x13" (8x33.3 cm) Bullnose
Names (colors) Andretti (brown)	UJ3B	UJ28	UHAN	UHAS	UHA6					UHA2
Armstrong (beige)	UJ3C	UJ29	UHAP	UHAT	UHA7					UHA3
Sampras (gray)	UJ3D	UJ3A	UHAQ	UHAU	UHA8					UHA4
Nickel						UJ66	UJ64	UJ62	UJ6N	
Bronze						UJ67	UJ65	UJ63	UJ6P	

Notes: Trim is available in all colors and made to complement Modular and Floor Tile. ** Suggested for interior applications only.

ASTM Test Results

Technical Characteristics	ANSI Standards	ASTM Test Results	ASTM Test Methods
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	7	MOHS Scale
Breaking Strength	≥ 250 lbf.	≥ 418 lbf.	C648
Facial Dimension	-3.0% < Nominal ≤ 3.0%	Within Standard	C499
Nominal Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (squareness)	+/- 0.50% or +/- 2.0 mm**	Within Standard	C502
Warpage (flatness)	+/- 0.75% or +/- 2.3 mm**	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
DCOF-Dynamic Coefficient of Friction (Wet Areas Only)†	As Reported	Minimum 0.42	DCOFAcuTest ^{SM*}
SCOF-Static Coefficient of Friction (Dry)	As Reported	0.70 ≤ S.C.O.F. < 0.80	C1028
SCOF-Static Coefficient of Friction (Wet)	As Reported	0.60 ≤ S.C.O.F. < 0.70	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

Tolynamic Coefficient of Friction (DCOF) - Water, oil, grease or other fluids create slippery conditions. When installing floors in areas with exposure to these conditions, a minimum D.C.O.F. value of 0.42 is required. Additionally, extra caution is required with regards to product selection and proper maintenance. Visit www.tcnatile.com for complete information regarding the DCOF Acutest test method and values.

DCOF Acutest is the industry designation for the test procedure contained in ANSI A137.1 Section 9.6, which has been extensively researched, allows for in-situ field measurements, and is in use at tile manufacturing facilities. It was so named to distinguish it from other DCOF measurements using different instruments and/or protocols.

