

MARAZZI  USA

the fine art of porcelain stoneware

(tosca)

glazed porcelain stoneware

Made In The USA



Tosca Amber



Tosca Beige



Tosca Ivory



Tosca Noce



Palace Listelli



| | MODULAR TILE | | | | FLOOR TILE | DECOS [†] | TRIMS [‡] |
|---------------------------------|-------------------------------|-------------------------------|-----------------------------|-------------------------------|---------------------------|------------------------------|---------------------------|
| Thickness | 6½" x 6½" (16.5 x 16.5 cm) | 6½" x 13" (16.5 x 33.3 cm) | 13" x 20" (33.3 x 50 cm) | 13" x 13" (33.3 x 33.3 cm) | 20" x 20" (50 x 50 cm) | 1¼" x 13" (3.2 x 33.3 cm) | 3" x 13" (8 x 33.3 cm) |
| | 7/16" (10.5mm) | 7/16" (10.5mm) | 7/16" (10.5mm) | 7/16" (10.5mm) | 7/16" (10.5mm) | Listelli | Bullnose |
| Names (colors) | | | | | | | |
| Tosca Amber (amber) | UB5D | UB5H | UB5R | UB5M | UB5V | | UB6M |
| Tosca Beige (beige) | UB5E | UB5J | UB5S | UB5N | UB5W | | UB6N |
| Tosca Ivory (ivory) | UB5F | UB5K | UB5T | UB5P | UB5X | | UB6P |
| Tosca Noce (walnut) | UB5G | UB5L | UB5U | UB5Q | UB5Y | | UB6Q |
| Palace (Complements all colors) | | | | | | AG3J | |

Notes: [†] Listelli Decos are imported, suggested for interior residential applications only, have a coefficient of friction less than 0.50 (wet), do not meet ADA recommendations and are made to complement Modular and Floor Tile.
[‡] Trim is available in all colors and made to complement Modular and Floor Tile.
^{***} Suggested for interior applications only.

ASTM Test Results

| Technical Characteristics | ASTM Standards | ASTM Test Results | ASTM Test Methods |
|--|---------------------------|----------------------|----------------------------|
| Water Absorption | ≤ 0.50% | ≤ 0.50% | C373 |
| Frost Resistance | As Reported | Resistant | C1026 |
| Scratch Resistance | MOHS 1-10 | 7 | MOHS Scale |
| Breaking Strength | ≥ 250 lbf. | ≥ 730 lbf. | C648 |
| Facial Dimension | -3.0% < Nominal ≤ 3.0% | Within Standard | C499 |
| Thickness | ≤ 0.04 in (1.02 mm max) | Within Standard | C499 |
| Wedging (squareness) | +/- 0.50% or +/- 2.0 mm** | Within Standard | C502 |
| Warpage (flatness) | +/- 0.75% or +/- 2.3 mm** | Within Standard | C485 |
| Abrasion Resistance | Class 0 - Class V | Class IV | C1027 |
| DCOF-Dynamic Coefficient of Friction (Wet Areas Only) [†] | As Reported | Less than 0.42 | DCOF AcuTest SM |
| SCOF-Static Coefficient of Friction (Dry) | As Reported | 0.60 ≤ C.O.F. < 0.70 | C1028 |
| SCOF-Static Coefficient of Friction (Wet) | As Reported | 0.50 ≤ C.O.F. < 0.60 | C1028 |
| Chemical Resistance | Class A - Class E | Class A | C650 |
| Stain Resistance | Class A - Class E | Class A | C1378 |

[†]Dynamic Coefficient of Friction (DCOF) - Water, oil, grease or other fluids create slippery conditions. When installing floors in areas with exposure to these conditions, a minimum D.C.O.F. value of 0.42 is required. Additionally, extra caution is required with regards to product selection and proper maintenance. Visit www.tnatie.com for complete information regarding the DCOF AcuTest test method and values.
SMDCOF AcuTest is the industry designation for the test procedure contained in ANSI A137.1 Section 9.6, which has been extensively researched, allows for in-situ field measurements, and is in use at tile manufacturing facilities. It was so named to distinguish it from other DCOF measurements using different instruments and/or protocols.
^{**} Whichever is less

