


Lava River



Lava River Mosaic - Square 2"x2"




Lost Sea



Lost Sea Mosaic - Square 2"x2"




Mammoth



Mammoth Mosaic - Square 2"x2"



Sequoyah



Sequoyah Mosaic - Square 2"x2"



Contributes to LEED Credits

made in the USA

ASTM Test Results

	MODULAR TILE		FLOOR TILE	DECOS	TRIMS
Thickness	6"x6" (15x15 cm) 3/8" (8 mm)	12"x12" (30x30 cm) 3/8" (8 mm)	18"x18" (45x45 cm) 3/8" (9 mm)	12"x12" (30x30 cm) Mosaic - Square 2"x2"	3"x12" (8x30 cm) Bullnose
Names (colors)	Lava River (Rust)	UL7U	UL7Y	UL84	UL88
	Lost Sea (Charcoal)	UL7V	UL7Z	UL85	UL89
	Mammoth (Brown)	UL7W	UL82	UL86	UL8A
	Sequoyah (Beige)	UL7X	UL83	UL87	UL8B

Notes: * Trim is available in all colors and made to complement Modular and Floor Tile.

Technical Characteristics	ANSI Standards	ASTM Test Results	ASTM Test Methods
Water Absorption	3.0% - 7.0%	2.0% - 5.0%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	7	MOHS Scale
Breaking Strength	≥ 250 lbf.	≥ 385 lbf.	C648
Facial Dimension	-3.0% < Nominal ≤ 3.0%	Within Standard	C499
Nominal Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (squareness)	+/- 0.50% or +/- 2.0 mm**	Within Standard	C502
Warpage (flatness)	+/- 0.75% or +/- 2.0 mm**	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class IV	C1027
DCOF-Dynamic Coefficient of Friction (Wet Areas Only)*	As Reported	Minimum 0.42	DCOF AcuTest SM
SCOF-Static Coefficient of Friction (Dry)	As Reported	0.70 ≤ S.C.O.F. < 0.80	C1028
SCOF-Static Coefficient of Friction (Wet)	As Reported	0.60 ≤ S.C.O.F. < 0.70	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

*Dynamic Coefficient of Friction (DCOF) - Water, oil, grease or other fluids create slippery conditions. When installing floors in areas with exposure to these conditions, a minimum D.C.O.F. value of 0.42 is required. Additionally, extra caution is required with regards to product selection and proper maintenance. Visit www.tcnatiles.com for complete information regarding the DCOF AcuTest test method and values.
 **DCOF AcuTest is the industry designation for the test procedure contained in ANSI A137.1 Section 9.6, which has been extensively researched, allows for in-situ field measurements, and is in use at tile manufacturing facilities. It was so named to distinguish it from other DCOF measurements using different instruments and/or protocols.
 ** Whichever is less

MARAZZI  USA

the fine art of porcelain stoneware

(stone age)

glazed ceramic tile

Made In The USA

