

Cork FLOATING FLOOR TECHNICAL SPECIFICATIONS

PROPERTY	REQUIREMENT
Length <600 mm >600 mm	+/- 0.3 mm =/- 1.0 mm
WIDTH	+/-0.25 mm
THICKNESS	+/-0.25 mm
DENSITY OF AGGLOMERATED CORK WEAR LAYER	> 450 Kg/m ³
MOISTURE CONTENT	< 8% max
BEHAVIOR OF THE BONDING	There Shall be No Delamination At All
COMPRESSION (ISO Norm 9148)	(%) 40/60
RECOVERY	(%) 50
HIGH DENSITY FIBERBOARD	>800 Kg/m ³
WEAR RESISTANCE (Loss Weight)	3.6 MG/100 CICLOS
SQUARENESS	< 0.3 mm
STRAIGHTNESS	< 0.3 mm
FLAMMABILTY	(Hardwood, Plywood, Veneer Association) Average Critical Radiant Flux 0.60 w/cm ²